

**Product Data Sheet**  
Edition 26/07/2007  
Identification no:  
02 05 01 01 002 0 000001  
Sikaflex® PRO-2 HP

## Sikaflex® PRO-2 HP

1-part low modulus polyurethane sealant for building joints

Construction

### Product Description

Sikaflex® PRO-2 HP is a one part, moisture curing, low modulus elastic joint sealant based on polyurethane. Suitable for movement and connection joints for indoor and outdoor applications.

### Uses

For movement joints in

- Precast concrete construction
- Balcony parapets
- Bridge cantilevers
- Retaining walls
- Subways

For caulking of

- Window sashes and doors
- Skirtings
- Wall/floor joints
- Shutter housings

### Characteristics / Advantages

- One-component, ready for use
- Bubble-free curing system
- Good adhesion to many substrates
- Short skinning time
- Good weathering – and aging properties
- Excellent workability, easy to use
- Can be over painted

### Tests

#### Approval / Standard

Contact with drinking water-based on British Standard 6920, Federal Specification TT-S-00230C and TT-S-00227E, ASTM C 920, ISO11600, Type F, Class 25 LM

### Product Data

#### Form

#### Colours

White, concrete grey, middle grey, dark grey, black

#### Packaging

600 ml sausage (20 sausages per box)

### Storage

#### Storage Conditions / Shelf-Life

15 months from date of production if stored in undamaged original sealed containers, in dry conditions and protected from direct sunlight at temperatures between +10°C and +25°C.



## Technical Data

|                            |   |                                |
|----------------------------|---|--------------------------------|
| <b>Chemical Base</b>       | 1-part polyurethane, moisture curing.   |                                |
| <b>Density</b>             | ~ 1.3 kg/l (colour concrete grey)       | (According to DIN 53 479)      |
| <b>Skinning Time</b>       | ~ 60 - 120 minutes (+23°C / 50% r.h.)   |                                |
| <b>Curing Rate</b>         | ~ 2 - 3 mm/24 h (+23°C / 50% r.h.)      |                                |
| <b>Movement Capability</b> | 25%                                     |                                |
| <b>Joint Dimensions</b>    | Min. width = 10 mm / max. width = 40 mm |                                |
| <b>Sag Flow</b>            | 0 mm, very good                         | (According to DIN EN ISO 7390) |
| <b>Service Temperature</b> | -40°C to +70°C                          |                                |

## Mechanical / Physical Properties

|                            |  |                                  |
|----------------------------|--|----------------------------------|
| <b>Tear Strength</b>       | ~ 7 N/mm (+23°C / 50% r.h.)  | (According to DIN 53 515)        |
| <b>Shore A Hardness</b>    | ~ 25 after 28 days (+23°C / 50% r.h.)  | (According to DIN 53 505)        |
| <b>E-Modulus</b>           | ~ 0.3 N/mm <sup>2</sup> at 100% elongation (+23°C / 50% r.h.) (According to DIN EN ISO 8340)<br>~ 0.6 N/mm <sup>2</sup> at 100% elongation (-20°C) |                                  |
| <b>Elongation at Break</b> | ~ 800% (+23°C / 50% r.h.)  | (According to DIN 53 504)        |
| <b>Elastic Recovery</b>    | > 80% (+23°C / 50% r.h.)   | (According to DIN EN ISO 7389 B) |

## System Information

### Application Details

#### Consumption / Joint Design

The joint width must be designed to suit the movement capability of the sealant. In general the joint width must be > 10 mm and < 40 mm. A width to depth ratio of ~ 2 : 1 must be maintained.

#### Standard design dimensions for concrete elements as per DIN 18 540 /table 3:

|                    |       |           |           |           |           |
|--------------------|-------|-----------|-----------|-----------|-----------|
| Joint distance     | 2 m   | 2 - 3.5 m | 3.5 - 5 m | 5 - 6.5 m | 6.5 - 8 m |
| Design joint width | 15 mm | 20 mm     | 25 mm     | 30 mm     | 35 mm     |
| Min. joint width   | 10 mm | 15 mm     | 20 mm     | 25 mm     | 30 mm     |
| Joint depth        | 8 mm  | 10 mm     | 12 mm     | 15 mm     | 15 mm     |

Minimum joint width for perimeter joints around windows: 10 mm

All joints must be properly designed and dimensioned by the specifier and the main contractor in accordance with the relevant standards, because changes are not usually feasible after construction. The basis for calculation of the necessary joint width are the technical values of the joint sealant and the adjacent building materials, plus the exposure of the building, its method of construction and its dimensions.

#### Approximate consumption

|                       |         |         |         |         |         |
|-----------------------|---------|---------|---------|---------|---------|
| Joint width           | 10 mm   | 15 mm   | 20 mm   | 25 mm   | 30 mm   |
| Joint depth           | 8 mm    | 8 mm    | 10 mm   | 12 mm   | 15 mm   |
| Joint length / 600 ml | ~ 7.5 m | ~ 4.5 m | ~ 2.5 m | ~ 1.6 m | ~ 1.3 m |

*Backing:* Use only closed cell, polyethylene foam backing rods.

#### Substrate Quality

Clean and dry, homogeneous, free from oils and grease, dust and loose or friable particles. Cement laitance must be removed.

|  |   |
|--|---|
| <b>Substrate Preparation / Priming</b> | <p><i>Non porous substrates:</i><br/>E.g. metals, powder coatings etc. have to be cleaned with a fine abrasive pad and Sika® Cleaner-205 by using a clean towel / cloth.<br/>After a flash off time of at least 15 min, apply Sika® Primer-3 N by using a brush.<br/>Before sealing allow a flash off time of at least 30 min. (max. 8 hrs.).<br/>For PVC use Sika® Primer-215.<br/>Before sealing allow a flash off time of at least 30 min. (max. 8 hrs.).</p> <p><i>Porous substrates:</i><br/>E. g concrete, aerated concrete and cementitious renders, mortars, brick, etc. have to be primed with Sika® Primer-3 N by using a brush.<br/>Before sealing allow a flash off time of at least 30 min. (max. 8 hrs.).</p> <p>Important note: Primers are only adhesion promoters. They neither substitute for the correct cleaning of the surface nor improve their strength significantly.</p> <p>Primers improve long term performance of a sealed joint.</p> <p>For further information refer to the Sika® Primer table.</p> |
|--|---|

### Application Conditions / Limitations

|                                   |                        |
|-----------------------------------|------------------------|
| <b>Substrate Temperature</b>      | +5°C min. / +40°C max. |
| <b>Ambient Temperature</b>        | +5°C min. / +40°C max. |
| <b>Substrate Moisture Content</b> | Dry                    |

### Application Instructions

|                                   |  |
|-----------------------------------|--|
| <b>Application Method / Tools</b> | <p>Sikaflex® PRO-2 HP is supplied ready to use.</p> <p>After suitable joint and substrate preparation, insert backing rod to required depth and apply primer if necessary. Insert cartridge into sealant gun and firmly extrude Sikaflex® PRO-2 HP into joint making sure that it is full contact with the side of the joint. Fill the joint, avoiding air entrapment. Sikaflex® PRO-2 HP must be tooled firmly against joint sides to ensure good adhesion.</p> <p>Masking tape must be used where sharp exact joint lines or exceptionally neat lines are required. Remove the tape whilst the sealant is still soft. Slick joint with smoothing liquid for a perfect sealant surface.</p> |
| <b>Cleaning of Tools</b>          | <p>Clean all tools and application equipment with Sika® Remover-208 / Sika® TopClean-T immediately after use. Hardened / cured material can only be mechanically removed.</p>  |

|   |  |
|---|--|
| <b>Notes on Application / Limitations</b> | <p>Elastic sealants may not be over painted.</p> <p>Compatible coatings may cover the joint sides to max. 1 mm.<br/>The compatibility must be tested according to DIN 52 452-2.</p> <p>Colour deviations may occur due to exposure to chemicals, high temperatures, UV-radiation (especially with colour shade white). However a change in colour will not adversely influence the technical performance or the durability of the product.</p> <p>Before using on natural stone contact our Technical Service.</p> <p>Do not use Sikaflex® PRO-2 HP as a glass sealer, on bituminous substrates, natural rubber, EPDM rubber or on building materials which might bleed oils, plasticisers or solvents which could attack the sealant.</p> <p>Do not use Sikaflex® PRO-2 HP to seal swimming pools.</p> <p>Not suitable for joints with water pressure or permanent water immersion.</p> <p>The freshly applied sealant has a smell similar to 'Amaretto' until it has fully cured (benzaldehyde).</p> <p><b>Do not mix with or expose uncured Sikaflex® PRO-2 HP to substances that may react with isocyanates, especially alcohols which are often components within e.g. thinners, solvents, cleaning agents and formwork releasing compounds. Such contact could interfere or prevent the cross linking curing reaction of the material.</b></p> |
|---|--|

---

**Value Base**

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

---

**Health and Safety Information**

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

---

**Legal Notes**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

---



Sika India Pvt. Ltd.  
Commercial Complex II  
620, Diamond Harbour Road  
Kolkata, 700 034, India

Phone +91 33 2447 2448/2449  
Telefax +91 33 2468 8688  
Ind.sika.com  
info@in.sika.com